

- **Woodchip for Pulping use**

• Specification (TAPPI Standard):	
28.6 MM – OVERSIZE	Not more than 5%
4.8 MM – 28.6 MM	Not less than 90%
9.5 MM – 22.2 MM	Not less than 55%
4.8 MM – UNDERSIZE	Not more than 5%
BARK and ROTTEN	Not more than 1%
• Moisture Content : 40%-50%	

• Specification (SCAN Standard):	
OVERSIZE 40.0 MM	5% Max in GMT
9.5 MM – 22.2 MM	55% Min in GMT **
4.8 MM – 9.5 MM	12% Max in GMT
4.8 MM – UNDERSIZE	3% Max in GMT
4.8 MM – 40.0 MM	92% Min in GMT **
ROT and BARK	1% Max in GMT
(** for reference only)	
• Moisture Content : 40%-50%	